

HANGZHOU HANHAO CHEMICAL CO., LTD

Plant: Jiangdong Development Zone, Great Jiangdong District, Hangzhou China

Office: 2103 Bldg1, Dacheng Plaza, Shixin Road, Xiaoshan, Hangzhou, China

Tel:+86-571-82502631/82551631 **Fax:**+86-571-82722631

TECHNICAL DATA SHEET

Product Description:

Product Name:	Benzidine Yellow GW-X
Color Index:	Pigment Yellow 12
C.I.No.	21090
CAS No.	6358-85-6
EC No.	229-355-1
Chemical Nature:	Disazo
Chemical Formula	$C_{32}H_{26}Cl_2N_6O_4$

Technical Properties:

A diarylide aniline yellow pigment, high opacity

Application:

Recommend: Water abased ink

Suggested for textile printing and water based paints.

Physical Properties

Density(g/cm3)	1.5
Moisture (%)	≤2.0
Water Soluble Matter	≤1.5
Oil Absorption (ml / 100g)	40-50
Electric conductivity (us/cm)	≤500
Fineness(80mesh)	≤5.0
PH value	6.0-7.0

Fastness Properties (5=Excellent, 1=Poor)

Acid Resistance	5	Soap Resistance	5
Alkali Resistance	5	Bleeding Resistance	4
Alcohol Resistance	5	Migration Resistance	-
Ester Resistance	4	Heat Resistance (°C)	160
Benzene Resistance	4	Light	5
Ketone Resistance	4	Fastness(8=Excellent)	

Note: The above information is provided as guidelines for your reference only.
The accurate effects should base on the test results in laboratory.