# HANGZHOU HANHAO CHEMICAL CO., LTD

Plant: Jiangdong Development Zone, Great Jiangdong District, Hangzhou China
Office: 2103 Bldg1, Dacheng Plaza, Shixin Road, Xiaoshan, Hangzhou, China
Tel:+86-571-82502631/82551631
Fax:+86-571-82722631

## TECHNICAL DATA SHEET

#### **Product Description:**

Product Name:	Permanent Yellow 3RLP	
Color Index:	Pigment Yellow 110	
C.I.No.	56280	
CAS No.	5590 <mark>-18-</mark> 1	
EC No.	226-9 <mark>99-5</mark>	
Chemical Nature:	Isoindolinone	
Chemical Formula	C <sub>22</sub> H <sub>6</sub> Cl <sub>8</sub> N <sub>4</sub> O <sub>2</sub>	

#### **Technical Properties:**

A reddish yellow pigment, with excellent processing stability, good dispersing ability, high transparency, excellent heat and outstanding fastness properties.

## **Application:**

Recommended for industrial paints, water based paints, solvent based paints, coil coatings, powder coatings, automotive paints.

Suggested for textile printing.

### **Physical Properties**

Density(g/cm3)	1.5
Moisture (%)	≤1.5
Water Soluble Matter	≤1.0
Oil Absorption (ml / 100g)	45-55
Electric conductivity (us/cm)	≤500
Fineness(80mesh)	≤5.0
PH value	6.5-7.5

#### Fastness Properties (5=Excellent, 1=Poor)

Acid Resistance	5	Soap Resistance	5
Alkali Resistance	5	<b>Bleeding Resistance</b>	5
Alcohol Resistance	5	Migration Resistance	5
Ester Resistance	5	Heat Resistance (°C)	280
Benzene Resistance	5	Light	8
Ketone Resistance	5	Fastness(8=Excellent)	

Note: The above information is provided as guidelines for your reference only.

The accurate effects should base on the test results in laboratory.

