HANGZHOU HANHAO CHEMICAL CO., LTD

Plant: Jiangdong Development Zone, Great Jiangdong District, Hangzhou China **Office:** 2103 Bldg1, Dacheng Plaza, Shixin Road, Xiaoshan, Hangzhou, China **Tel:**+86-571-82502631/82551631 **Fax:**+86-571-82722631

TECHNICAL DATA SHEET

Product Description:

Color Index: Solvent Orange 7

C.I.No. 12140
CAS No. 3118-97-65
Chemical Family Monoazo Series
Chemical Formula $C_{18}H_{16}N_2O$

Technical Properties:

With deep reddish shade and transparent. With good heat resistance, good light fastness and migration resistance. It has bright color in plastic.

Application: ("☆" Superior, "○" Applicable, "△" Not recommend

PS	HIPS	ABS	PC	RPVC	PMMA	SAN	AS	PA6	PET
☆	☆	⋫	☆	☆	☆	☆	⋫	☆	☆

Also used in candles, inks, particularly to the staining of petroleum products, as well as to brightening agents.

Physical Properties

Density(g/cm3)	Melting	Light fastness	Recommended Dosage		
	Point(℃)	(in PS)	Transparent	Nontransparent	
0.34	133	7	0.025	0.05	

Light Fastness: Consist of 1st to 8th grade, and the 8th grade is superior, the 1st grade is bad.

The heat resistance in PS can reach to 300℃

Degree of pigmentation: 0.05% dyes+0.1%titanium dioxide R

Solvent orange 7 solubility in organic solvent at $20^{\circ}C(g/l)$

Acetone	Butyl Acetate	Methylbenzene	Dichloromethane	Ethylalcohol
6	12	40	120	4

Note: The above information is provided as guidelines for your reference only. The accurate effects should base on the test results in laboratory.