

HANGZHOU HANHAO CHEMICAL CO., LTD

Plant: Jiangdong Development Zone, Great Jiangdong District, Hangzhou China

Office: 2103 Bldg1, Dacheng Plaza, Shixin Road, Xiaoshan, Hangzhou, China

Tel:+86-571-82502631/82551631 **Fax:**+86-571-82722631

TECHNICAL DATA SHEET

Product Description:

Color Index:	Solvent Red 179
C.I.No.	564150
CAS No.	89106-95-5/6829-22-7
EC NO.	229-904-5
Chemical Family	Ketoamine Series
Chemical Formula	C ₂₂ H ₁₂ N ₂ O

Technical Properties:

The product is yellowish transparent red oil solvent dye. It is of good heat resistance and light resistance, good migration resistance and high tinting strength.

Application: (“☆” Superior, “○” Applicable, “△” Not recommend

PS	HIPS	ABS	PC	RPVC	PMMA	SAN	AS	PA6	PET
☆	☆	☆	☆	☆	☆	☆	☆	○	○

Also used in coloring resin and fibre, and has a better solubility than transparent red EG.

Physical Properties

Density(g/cm3)	Melting Point(°C)	Light fastness (in PS)	Recommended Dosage	
			Transparent	Nontransparent
0.27	251	8	0.05	0.3

Light Fastness: Consist of 1st to 8th grade, and the 8th grade is superior, the 1st grade is bad.

The heat resistance in PS can reach to 300℃

Degree of pigmentation: 0.05% dyes+0.1% titanium dioxide R

Solvent red 179 solubility in organic solvent at 20℃(g/l)

Acetone	Butyl Acetate	Methylbenzene	Dichloromethane	Ethylalcohol
1.6	1.6	4.1	8	0.9

Note: The above information is provided as guidelines for your reference only.
The accurate effects should base on the test results in laboratory.