HANGZHOU HANHAO CHEMICAL CO., LTD

Plant: Jiangdong Development Zone, Great Jiangdong District, Hangzhou China
Office: 2103 Bldg1, Dacheng Plaza, Shixin Road, Xiaoshan, Hangzhou, China
Tel:+86-571-82502631/82551631
Fax:+86-571-82722631

TECHNICAL DATA SHEET

Product Description:

Color Index:	Solvent Red 195			
CAS No.	164251 <mark>-88-1</mark>			
Chemical Family	Sulph <mark>onazo Series</mark>			

Technical Properties:

The product is deep red transparent oil solvent dye. It is of good heat resistance, good light fastness and hiht tinting strength and bright color.

Application: ("☆" Superior, "O" Applicable, "△" Not recommend

PS	HIPS	ABS	PC	RPVC	PMMA	SAN	AS	PA6	PET
☆	☆	\$	☆	☆	☆	\$≍	☆	0	0

Physical Properties

Density(g/cm3)	Melting	Light fastness	Recommended Dosage	
	Point(°C)	(in PS)	Transparent	Nontransparent
0.39	216	8	0.005	0.01

Light Fastness: Consist of 1st to 8th grade, and the 8th grade is superior, the 1st grade is bad.

The heat resistance in PS can reach to 300 °C

Degree of pigmentation: 0.05% dyes+0.1% titanium dioxide R

Solvent red 195 solubility in organic solvent at 20°C(g/l)

Acetone	Butyl Acetate	Methylb <mark>enze</mark> ne	Dichloromethane	Ethylalcohol
1.4	1.3	2.7	37.1	0.8

Note: The above information is provided as guidelines for your reference only. The accurate effects should base on the test results in laboratory.