# HANGZHOU HANHAO CHEMICAL CO., LTD

Plant: Jiangdong Development Zone, Great Jiangdong District, Hangzhou China
Office: 2103 Bldg1, Dacheng Plaza, Shixin Road, Xiaoshan, Hangzhou, China
Tel:+86-571-82502631/82551631
Fax:+86-571-82722631

## TECHNICAL DATA SHEET

### **Product Description:**

Color Index:	Solvent Violet 31
C.I.No.	61102
CAS No.	7095 <mark>6-27-3</mark>
Chemical Family	Anthraquinone Series
Chemical Formula	$C_{14}H_8Cl_2N_2O_2$

#### **Technical Properties:**

The product is reddish bright violet oil solvent dye. It is of good heat resistance and light resistance, high tinting strength with bright color.

### Application: (" $\updownarrow$ " Superior, " $\bigcirc$ " Applicable, " $\triangle$ " Not recommend

PS	HIPS	ABS	PC	RPVC	PMMA	SAN	AS	PA6	PET
☆	☆	☆	0	☆	☆	☆	☆	-	$\Delta$

#### **Physical Properties**

Density(g/cm3)	Melting	Light fastness	Recommended Dosage	
	Point(°C)	(in PS)	Transparent Nontranspa	
0.54	282	6-7	0.025	0.05

Light Fastness: Consist of 1<sup>st</sup> to 8<sup>th</sup> grade, and the 8<sup>th</sup> grade is superior, the 1<sup>st</sup> grade is bad.

#### The heat resistance in PS can reach to 260°C

Degree of pigmentation: 0.05% dyes+0.1%titanium dioxide R

#### Solvent violet 31 solubility in organic solvent at 20°C(g/l)

Acetone	Butyl Acetate	Methylbenzene	Dichloromethane	Ethylalcohol
20	18	20	40	1

Note: The above information is provided as guidelines for your reference only. The accurate effects should base on the test results in laboratory.